

DEPARTMENT OF TRANSPORTATION
DIVISION OF ENGINEERING SERVICES
Transportation Laboratory
5900 Folsom Blvd.
Sacramento, California 95819-4612



METHOD OF TEST FOR THE SOUNDNESS OF AGGREGATES BY USE OF SODIUM SULFATE

A. SCOPE

This test method describes the procedure to be followed when testing aggregates to determine their resistance to disintegration by saturated solutions of sodium sulfate.

B. REFERENCES

California Test 202 – Sieve Analysis of Fine and Coarse Aggregate
California Test 226 – Determination of Moisture Content by Oven Drying
AASHTO T 104 – Soundness of Aggregate by Use of Sodium Sulfate or Magnesium Sulfate
AASHTO M 92 – Wire-Cloth Sieves for Testing Purposes

C. APPARATUS

1. Sieves: standard sieves conforming to AASHTO M 92. The sieves sizes are: 2½ in., 2 in., 1½ in., 1 in., ¾ in., ½ in., ⅜ in., ¼ in., No. 4, No. 8, No. 16, No. 30, No. 50, No. 100, and No. 200.
2. Sieve Shaker: a mechanical sieve shaker must conform to the requirements for thoroughness of sieving as defined in California Test 202.
3. Sample Containers: wire screen baskets for immersing the aggregate samples in the solution. The wire screen and frames must be made of corrosion-resistant metal such as brass, bronze, or stainless steel. The openings in the screen must be smaller than the openings of the sieve that will be used to determine the percent loss at the end of the test. Sample baskets must have a bail suitable for suspending them from brackets while in the solution and in the oven.
4. Balance: a 25-kg or larger balance or scale sensitive to 0.1 % of the sample weight.
5. Oven: a vented, forced-draft oven capable of maintaining a temperature of 230°F ± 9°F. The interior of the oven must be equipped with racks designed to suspend the sample baskets above the shelves allowing free circulation of air around and under the baskets.
6. Tank: a suitable solution container for immersing samples. The container must be of such height that the solution covers the samples in the sample containers to a depth of at least ½ in. and of such capacity that it will hold a volume of solution equal to at least 5 times the total volume of the samples immersed at any one time. Protection against the accidental addition of extraneous substances must be provided. An enclosed cabinet housing the immersion tank or individual covers over the sample baskets are both satisfactory methods of protection.

D. MATERIALS

1. Prepare a saturated sodium sulfate solution by dissolving a C.P., U.S.P., or equal grade of salt in water at a temperature of 77°F to 86°F.
2. Add sufficient salt of either the anhydrous (Na_2SO_4) or the crystalline ($\text{Na}_2\text{SO}_4 \cdot 10\text{H}_2\text{O}$) form to ensure not only saturation but also the presence of excess crystals when the solution is ready for use in the tests. Thoroughly stir the mixture during the addition of the salt. Frequently stir the solution until used. Cool the solution to a temperature of $70^\circ\text{F} \pm 2^\circ\text{F}$ and maintain it at the temperature for at least 48 hr before use. Thoroughly stir the solution immediately before use. When used, the solution must have a specific gravity of not less than 1.151 and not greater than 1.174.

For the solution, 215 g of anhydrous salt or 700 g of the decahydrate per liter of water are sufficient for saturation at 72°F. However, since these salts are not completely stable and since it is desirable that an excess of crystals be present, the use of not less than 225 g of the anhydrous salt or 750 g of the decahydrate salt for each liter of water is recommended.

3. Barium Chloride: approximately 10 % solution is required.

E. CONTROL

Maintain the temperature of the solution at $70^\circ\text{F} \pm 2^\circ\text{F}$ during testing.

F. PREPARATION OF SAMPLE

1. Fine Aggregate.
 - a. Split or quarter a representative portion of material of sufficient size to yield not less than 100 g of each of the following sizes after washing:

Passing Sieve Size	Retained Sieve Size
No. 4	No. 8
No. 8	No. 16
No. 16	No. 30
No. 30	No. 50
No. 50	No. 100

- b. Wash the sample to remove all coatings. Washing may be done by any means which will accomplish thorough cleaning without degrading the material. Inundating the sample in a pan of water and stirring by hand is an accepted method. Continue washing until the water passing through or being poured off the sample is clear. Pass all wash water through a No. 100 sieve and return all material retained on the sieve to the sample.
 - c. Oven-dry the sample to constant weight at $230^\circ\text{F} \pm 9^\circ\text{F}$ in accordance with California Test 226 and cool to room temperature.
 - d. Divide the sample into representative portions for sieving.
 - e. Sieve the individual portions to refusal on the sieves listed above until the required 100 g fractions are obtained. Do not use the aggregate sticking in the meshes of the sieves.

- f. Weigh out 100 g test portions from each aggregate size and place in separate sample containers.
2. Coarse Aggregate.
- a. Separate the aggregate on the sieve sizes listed in C.1. and determine the amount of each size fraction.
 - b. Split or quarter a test portion meeting the weight requirements shown below for each size fraction which makes up 5 % or more of the submitted sample.

Weight of Test Portions

Schedule B

Aggregate Size		Weight* (g)
Passing Sieve Size	Retained Sieve Size	
2½ in.	2 in.	3000
2 in.	1½ in.	2000
1½ in.	1 in.	1500
1 in.	¾ in.	1000
¾ in.	½ in.	750
½ in.	⅜ in.	500
⅜ in.	No. 4	300

Schedule A

Aggregate Size		Weight* (g)
Passing Sieve Size	Retained Sieve Size	
2½ in.	2 in.	24 000
2 in.	1½ in.	16 000
1½ in.	1 in.	12 000
1 in.	¾ in.	2000
¾ in.	½ in.	1500
½ in.	⅜ in.	1000
⅜ in.	No. 4	600

* The weight of the test portion may be reduced according to Schedule B when the soundness loss on the previous sample from the same source is less than 5 %. Retest any material tested according to weight Schedule B using the weight specified in Schedule A when the determined loss is 5 % or more. Test all sources for which previous test data is not available according to Schedule A.

- c. Wash the individual test portions to remove all coatings.
- d. Oven-dry the samples to constant weight at 230°F ± 9°F in accordance with California Test 226 and cool to room temperature.
- e. Re-sieve each test portion to refusal on the respective retaining sieve.
- f. Weigh and record each test portion and place in separate sample containers.

G. TEST PROCEDURE

1. Immerse the test samples in the sodium sulfate solution for 17 hr ± 1 hr. Suspend the sample containers from racks over the tank in such a manner that the solution covers the samples to a minimum depth of ½ in.
2. Remove the samples from the solution and drain for about 15 min.
3. Oven-dry the samples to constant weight at 230°F ± 9°F in accordance with California Test 226 and cool to room temperature.
 - a. Suspend the sample containers from the racks in the oven.
 - b. Do not use the oven for any other purpose while it is being used to dry soundness test samples.
4. Repeat the immersion, drying, and cooling for a total of 5 complete cycles.
5. After completion of the fifth cycle, immerse the test samples in a continuous flow of fresh water at 110°F ± 10°F until all of the sodium sulfate has been removed.

NOTE: The presence of sodium sulfate in the wash water can be detected by the reaction of the wash water with barium chloride (BaCl₂). Cloudiness indicates the presence of sodium sulfate.

6. Oven-dry to constant weight at 230°F ± 9°F in accordance with California Test 226 and cool to room temperature.
7. Sieve each sample to refusal over a sieve having square openings half the size of the sieve on which the aggregate was originally retained. Weigh the particles retained on this sieve and record the weight.

H. CALCULATION OF SOUNDNESS LOSS

1. Individual Test Portions.
 - a. Compute the Percentage Loss for each test portion using the equation:

$$\text{Percentage Loss} = \left[\frac{W_o - W_f}{W_o} \right] \times 100$$

Where: W_o = Original weight of the test sample, to the nearest 1 g

W_f = Weight of aggregate retained on the half size sieve after the sample has been tested, to the nearest 1 g

- b. Consider size fractions which amount to less than 5 % of the total sample to have the same loss as the average of the next smaller and next larger sizes. If one of these sizes is absent, use the loss of the portion which is present.

2. Weighted Average Loss of Coarse Aggregate.
 - a. Determine the total sample percentage that each size fraction represents.
 - b. Multiply the percent for each size by the percentage loss determined for that size.
 - c. To determine the weighted average percentage loss of the sample, divide the sum of the products for the percent of each size and its respective percent loss by the sum of the percents for each size.

Example:

Size Fractions in Sample	A Percentage of Each Size in "As Received" Grading	B Individual Percent Loss	A × B
1 in. × ¾ in.	4*	7.5**	30.0
¾ in. × ½ in.	32	7.5	240.0
½ in. × ⅜ in.	24	6.4	153.6
⅜ in. × No. 4	35	8.0	280.0
Total	95	--	703.6

* Not tested - size represents less than 5 % of total sample.

** See Section H.1.b.

$$\text{Weighted Average Percent Loss} = \frac{703.6}{95} = 7.4$$

3. Batch Soundness Loss of Coarse Aggregate.
 - a. The batch soundness loss is the combined loss of each primary size of coarse aggregate being used in the mix.
 - b. The batch soundness loss may be used only when the loss for 1 primary size exceeds the maximum allowable loss by not more than 2 %.
 - c. Calculate the batch soundness loss using the weighted average basis shown below regardless of the actual proportions to be used.

2½ in. Maximum	
2½ in. × 1½ in.	34 %
1½ in. × ¾ in.	33 %
1 in. × No. 4	33 %

1½ in. Maximum	
1½ in. × ¾ in.	67 %
1 in. × No. 4	33 %

Example:

Primary Aggregate Size	A Percent Loss	B Weighted Percentage	A × B
1½ in. × ¾ in.	11.8	67	7.9
1 in. × No. 4	6.1	33	2.0
Batch Soundness Loss			9.9

4. Weighted Average Loss of Fine Aggregate.
- a. Use the following standard size distribution regardless of the actual sample grading:

Size Fraction	Percent of Total Sample
No. 4 × No. 8	22
No. 8 × No. 16	19
No. 16 × No. 30	24
No. 30 × No. 50	20
No. 50 × No. 100	15

- b. Multiply the loss determined for each size by the percent of the total sample shown in “a” above and divide the product by 100 to determine the loss of each fraction as a percentage of the total sample.
- c. Example:

Size Fraction	Percent of Total Sample	Individual Percent Loss	Percent Loss on Total Sample Basis
No. 4 × No. 8	22	4.7	1.0
No. 8 × No. 16	19	4.2	0.8
No. 16 × No. 30	24	3.6	0.9
No. 30 × No. 50	20	4.0	0.8
No. 50 × No. 100	15	8.1	1.2
Weighted Average Percent Loss			4.7

I. REPORTING TEST RESULTS

Report the Weighted Average Percent Loss for the coarse and fine aggregate and the Batch Soundness Loss when necessary. When reporting the Batch Soundness Loss include the Test Number and Soundness Loss of each primary size of coarse aggregate used in the computation.

J. PRECAUTIONS

1. Be sure that the aggregate is both clean and dry prior to subjecting it to the first cycle of the test because the solution must have free access to any cracks or crevices in the aggregate particles.

2. The aggregate must be completely dried during the drying phases of the test procedure.
3. Do not place aggregate in the solution until it has cooled to room temperature. Some aggregates may split and disintegrate when subjected to sudden temperature changes, and warm aggregate can cause objectionable increases in the temperature of the sodium sulfate solution.
4. Be sure to use sample baskets with openings smaller than the openings of the sieve that will be used at the end of the test for the determination of the percent loss.
5. Check both the specific gravity and the temperature of the solution daily, as test reproducibility will be seriously affected if the specific gravity and/or the temperature are allowed to vary from the specified requirements.

K. HEALTH AND SAFETY

It is the responsibility of the user of this test method to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. Prior to handling, testing or disposing of any materials, testers must be knowledgeable about safe laboratory practices, hazards and exposure, chemical procurement and storage, and personal protective apparel and equipment.

Caltrans Laboratory Safety Manual is available at:

http://www.dot.ca.gov/hq/esc/ctms/pdf/lab_safety_manual.pdf

**End of Text
(California Test 214 contains 7 Pages)**